


Butanox[®] M-50

Product description

Methyl ethyl ketone peroxide, solution in dimethyl phthalate



CAS No. : 1338-23-4
 EINECS/ELINCS No. : 215-661-2
 TSCA status : listed on inventory

Specifications

Appearance : Clear and colorless liquid
 Total active oxygen : 8.8-9.0%

Characteristics

Density, 20°C : 1.180 g/cm³
 Viscosity, 20°C : 24 mPa.s
 Water content : 3.0%

Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Akzo Nobel recommends a maximum storage temperature (T_s max.) for each organic peroxide.

For *Butanox* M-50 T_s max. = 25°C

When stored under the recommended storage conditions, *Butanox* M-50 will remain within the Akzo Nobel specifications for a period of at least three months after delivery.

Thermal stability

Organic peroxides are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

For *Butanox* M-50 SADT : 60°C
 Emergency temperature (T_{em}) : 55°C
 No control temperature (T_c) required

The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).

Major decomposition products

Carbon dioxide, Water, Acetic acid, Formic acid, Propanoic acid, Methyl ethyl ketone

Packaging and transport

The standard packaging is a 30 l Nourytainer® for 30 kg peroxide solution.

Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Akzo Nobel representative.

Butanox M-50 is classified as Organic peroxide type D; liquid; Division 5.2; UN 3105; PG II.

Safety and handling

Keep containers tightly closed. Store and handle *Butanox* M-50 in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room.

Avoid contact with reducing agents (e.g. amines), acids, alkalis and heavy metal compounds (e.g. accelerators, driers and metal soaps).

Please refer to the Material Safety Data Sheet (MSDS) for further information on the safe storage, use and handling of *Butanox* M-50. This information should be thoroughly reviewed prior to acceptance of this product.

The MSDS is available at www.akzonobel-polymerchemicals.com.

Applications

Butanox M-50 is a general purpose methyl ethyl ketone peroxide (MEKP) for the curing of unsaturated polyester resins in the presence of a cobalt accelerator at room and elevated temperatures.

The curing system *Butanox* M-50/cobalt accelerator is particularly suitable for the curing of gelcoat resins, laminating resins, lacquers and castings; moreover the manufacture of light resistant parts may be possible contrary to the curing system benzoyl peroxide/amine accelerator.

Practical experience throughout many years has proven that by the guaranteed low water content and the absence of polar compounds in *Butanox* M-50, this peroxide is very suitable in GRP products for e.g. marine applications.

For room temperature application it is necessary to use *Butanox* M-50 together with a cobalt accelerator (e.g. Accelerator NL-49P).

Dosing

Depending on working conditions, the following peroxide and accelerator dosage levels are recommended:

<i>Butanox</i> M-50	1 - 4 phr [*]
Accelerator NL-49P	0.5 - 3 phr

Cure Characteristics

In a high reactive standard orthophthalic resin in combination with Accelerator NL-49P (= 1% cobalt) the following application characteristics were determined:

Gel times at 20°C

2 phr <i>Butanox</i> M-50 + 0.5 phr Accelerator NL-49P	12 minutes
2 phr <i>Butanox</i> M-50 + 1.0 phr Accelerator NL-49P	7 minutes

Cure of 1 mm pure resin layer at 20°C

The speed of cure is expressed as the time to reach a Persoz hardness of respectively 30, 60 and 120 s.

	Persoz: 30	60	120	s
2 phr <i>Butanox</i> M-50 + 0.5 phr Accelerator NL-49P	2.4	4.1	13	h
2 phr <i>Butanox</i> M-50 + 1.0 phr Accelerator NL-49P	1.7	3.0	9.5	h

^{*} phr = parts per hundred resin

Cure of 4 mm laminates at 20°C

4 mm laminates have been made with a 450 g/m² glass chopped strand mat. The glass content in the laminates is 30% (w/w).

The following parameters were determined:

- Time-temperature curve.
- Speed of cure expressed as the time to achieve a Barcol hardness (934-1) of 0-5 and 25-30 respectively.
- Residual styrene content after 24 h at 20°C and a subsequent postcure of 8 h at 80°C.

	Gel time (min.)	Time to Peak (min.)	Peak exotherm (°C)
2 phr <i>Butanox</i> M-50 + 0.5 phr Accelerator NL-49P	13	36	44
2 phr <i>Butanox</i> M-50 + 1.0 phr Accelerator NL-49P	8	26	64

	Barcol 0-5 (h)	Barcol 25-30 (h)	Res. styrene 24 h 20°C (%)	Res. styrene + 8 h 80°C (%)
2 phr <i>Butanox</i> M-50 + 0.5 phr Accelerator NL-49P	3	15	6	0.3
2 phr <i>Butanox</i> M-50 + 1.0 phr Accelerator NL-49P		1	5	0.1

Pot life at 20°C

Pot lives were determined of a mixture of *Butanox* M-50 and a non-preaccelerated UP resin at 20°C.

2 phr <i>Butanox</i> M-50	12 h
4 phr <i>Butanox</i> M-50	7 h

Solubility

Butanox M-50 is miscible with phthalates and slightly miscible with water.

Colors

Butanox M-50 is available in the colors blue, yellow-A, red-YM and red-YM 1/6.

Butanox and *Nouryainer* are registered trademarks of Akzo Nobel Chemicals BV or affiliates.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Akzo Nobel Polymer Chemicals, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nothing contained herein shall be construed as granting or extending any license under any patent. Buyer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued bulletins on the subject matter covered. The user may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. You may not copy this document to a website.



Akzo Nobel Polymer Chemicals BV
Amersfoort, The Netherlands
Tel. +31 33 467 6767
Fax +31 33 467 6151

polymerchemicals.nl@akzonobel-pc.com

Akzo Nobel Polymer Chemicals LLC
Chicago, U.S.A.
Tel. +1 312 544 7000
1 800 828 7929 (Toll free US only)
Fax +1 312 544 7188

polymerchemicals.na@akzonobel-pc.com

Akzo Nobel Polymer Chemicals Ltd.
Shanghai, PR China
Tel. +86 21 6279 3399
Fax +86 21 6247 1129

polymerchemicals.ap@akzonobel.com

www.akzonobel-polymerchemicals.com

ROW TC 65421.04/October 2003