



Potters Hollow Spheres

TYPICAL PROPERTIES

TYPICAL PROPERTIES OF Q-CEL® HOLLOW SPHERES					
Product	Density		Particle Size (Microtrac)		Maximum Working Pressure (psi)
	Bulk (g/cm ³)	Effective (g/cm ³)	Mean (µm)	Range (µm)	
300	0.12	0.21	90	5-200	500
6014	0.08	0.14	85	5-200	250
6019	0.11	0.19	75	5-175	500
6028	0.16	0.28	70	5-150	750
6036	0.21	0.36	60	5-125	1,000
6042	0.24	0.42	55	5-110	2,000
6048	0.27	0.48	50	5-100	3,000

For More Information: Call 1-800-55 BEADS

Visit our Web site: www.pottersbeads.com



Q-CEL® is a registered trademark of Potters Industries, Inc.

Although the information and suggestions in this brochure ("information") are believed to be correct, Potters Industries Inc. makes no representations or warranties as to the completeness or accuracy of the information. The information is supplied upon the following conditions: The persons receiving the information will determine its suitability for their purposes; Potters Industries Inc. will not be responsible for damages of any nature whatsoever resulting from the use of, or reliance upon, the information or the materials, devices or products to which the information refers; No information is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent; Potters Industries Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent; and NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE MATERIALS, DEVICES OR PRODUCTS TO WHICH THE INFORMATION REFERS.

© 2004 Potters Industries Inc.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means electronic, mechanical, photocopying, recording or otherwise, without the prior permission of the publisher and copyright holder.

PA002/8.06